



## Vuurvast mortels

vuurvaste mortel

### Blakite

voegen van 1-2 mm

vuurvast : < 1650° C

#### chemische analyse (%)

| Anorthiet<br>CaAl <sub>2</sub> Si <sub>2</sub> O <sub>8</sub> | klei       | Natriumsilicaat<br>molverhouding >3,2<br>Na <sub>2</sub> SiO <sub>3</sub> | Aluminiumoxide<br>Al <sub>2</sub> O <sub>3</sub> | andere     |
|---|------------|---|--|------------|
| 30-70   | 5-40       | 20-30   | 0-20   | <3         |
| blakite   | 20kg/emmer | < 10 stuks  |  | € 42,46 st |

**Producent : THERMAL CERAMICS BENELUX B.V.**

**Beschrijving : Deze producten zijn metselspecies met een zeer hoge temperatuur bestendigheid. Bevat alkaline vloeistof en kan de huid irriteren evenals oogschade veroorzaken. Blootstelling kan resulteren in milde, mechanische irritatie aan huid, ogen en bovenste luchtwegen. effecten zijn doorgaans van tijdelijke aard.**

#### Blakite

This is a highly refractory mortar, dark grey in colour, which has a high water retention characteristic. It was specially developed for laying insulating firebricks but is also suitable for use with super duty and high alumina dense refractory bricks, at operating temperatures up to 1650°C. It is supplied in a consistency suitable for shallow patching or trowelling but requires the addition of approximately 5% water for dipping. Blakite is a good choice as a single, general purpose mortar on projects involving mainly insulating firebricks but also including some dense firebricks.

#### Prijzen excl. btw en transport

Deze informatie kan niet als contractuele specificatie worden beschouwd.